



## Aluminium bronze - UNI EN 1982:2017

Classification	Alloy name		Cu	Pb	Sn	Fe	Al	Ni	Mn	Sb	P	Si	Zn	S	As	Bi	Cd	Cr	Mg	Co	Se
UNI EN 1982:2017	CB333G (12)	min	76	-	-	4	8.8	4	-	-	-	-	-	-	-	-	-	-	-	-	-
		max	82.5	0.03	0.1	5.3	10	5.5	2.5	-	-	0.1	0.4	-	-	0.01	-	0.05	0.05	-	-

### Notes

12 For permanent mould castings, the minimum iron content of ingots and castings shall be 3.0% and the minimum nickel content shall be 3.7%