



Ottone per arte - RMG STANDARD

Classificazione	Lega		Cu	Pb	Sn	Fe	Al	Ni	Mn	Sb	P	Si	Zn	S	As	Bi	Cd	Cr	Mg	Co	Se	
RMG STANDARD	DELTAB/MOD	min	59	-	-	-	0.4	-	-	-	-	-	20	-	-	-	-	-	-	-	-	-
		max	61	1.5	0.8	0.45	0.5	0.7	0.5	-	-	0.1	40	-	-	-	-	-	-	-	-	-