



Ottone - JIS H 2202:2016

Classificazione	Lega		Cu	Pb	Sn	Fe	Al	Ni	Mn	Sb	P	Si	Zn	S	As	Bi	Cd	Cr	Mg	Co	Se	
JIS H 2202:2016	CACIN201	min	83	-	-	-	-	-	-	-	-	-	10	-	-	-	-	-	-	-	-	-
		max	88	0.5	0.1	0.2	0.2	0.2	-	-	-	-	-	20	-	-	-	-	-	-	-	-