



Ottone - JIS H 2202:2016

Classificazione	Lega		Cu	Pb	Sn	Fe	Al	Ni	Mn	Sb	P	Si	Zn	S	As	Bi	Cd	Cr	Mg	Co	Se
JIS H 2202:2016	CACIN203	min	58	0.5	-	-	-	-	-	-	-	-	20	-	-	-	-	-	-	-	-
		max	64	3	1	0.6	0.5	1	-	-	-	-	50	-	-	-	-	-	-	-	-