

**Ottone - JIS H 2202:2016**

Classificazione	Lega		Cu	Pb	Sn	Fe	Al	Ni	Mn	Sb	P	Si	Zn	S	As	Bi	Cd	Cr	Mg	Co	Se
JIS H 2202:2016	CACIN211	min	65.5	0.1	1.1	-	0.01	-	-	0.06	0.05	-	20	-	-	-	-	-	-	-	-
		max	68.5	2	1.5	0.2	0.1	0.2	-	0.15	0.1	0.05	40	-	-	-	-	-	-	-	-