



Ottone al bismuto - JIS H 2202:2016

Classificazione	Lega		Cu	Pb	Sn	Fe	Al	Ni	Mn	Sb	P	Si	Zn	S	As	Bi	Cd	Cr	Mg	Co	Se
JIS H 2202:2016	CACIN232	min	66	-	0.6	-	0.35	-	-	0.02	-	0.4	20	-	-	0.5	-	-	-	-	-
		max	72	0.09	1.1	0.2	0.6	0.2	0.2	0.2	0.03	0.8	40	-	-	0.8	-	-	-	-	-