



## Ottone per arte - RMG STANDARD

Classificazione	Lega		Cu	Pb	Sn	Fe	Al	Ni	Mn	Sb	P	Si	Zn	S	As	Bi	Cd	Cr	Mg	Co	Se	
RMG STANDARD	G3	min	59.5	1.5	-	-	-	-	-	-	-	-	20	-	-	-	-	-	-	-	-	-
		max	62	2.5	1	0.7	1	1.2	0.5	-	-	0.2	40	-	-	-	-	-	-	-	-	-