



Ottone - UNI EN 1982:2017

Classificazione	Lega		Cu	Pb	Sn	Fe	Al	Ni	Mn	Sb	P	Si	Zn	S	As	Bi	Cd	Cr	Mg	Co	Se
UNI EN 1982:2017	CB751S (2)	min	63.5	0.8	-	0.25	-	-	-	-	-	0.7	20	-	-	-	-	-	-	-	-
		max	65.5	2	0.8	0.5	0.1	0.8	0.1	0.05	-	1	40	-	-	-	-	-	-	-	-

Note

2 Nickel incluso nel conteggio del rame