



Bronzo ad alto tenore di piombo - UNI EN 1982:2017

Classificazione	Lega		Cu	Pb	Sn	Fe	Al	Ni	Mn	Sb	P	Si	Zn	S	As	Bi	Cd	Cr	Mg	Co	Se
UNI EN 1982:2017	CB495K (2)	min	78	8.2	9.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
		max	81.5	10.5	11	0.2	0.01	2	0.2	0.5	0.1	0.01	2	0.08	-	-	-	-	-	-	-

Note

2 Nickel incluso nel conteggio del rame