



## Bronzo ad alto tenore di piombo - UNI EN 1982:2017

Classificazione	Lega		Cu	Pb	Sn	Fe	Al	Ni	Mn	Sb	P	Si	Zn	S	As	Bi	Cd	Cr	Mg	Co	Se
UNI EN 1982:2017	CB497K (2)	min	70	19	4.2	-	-	0.5	-	-	-	-	-	-	-	-	-	-	-	-	-
		max	77.5	23	6	0.2	0.01	2.5	0.2	0.75	0.1	0.01	2	0.08	-	-	-	-	-	-	-

### Note

2 Nickel incluso nel conteggio del rame