



Ottone - UNI EN 1982:2017

Classificazione	Lega		Cu	Pb	Sn	Fe	Al	Ni	Mn	Sb	P	Si	Zn	S	As	Bi	Cd	Cr	Mg	Co	Se
UNI EN 1982:2017	CB766S (2)	min	60	-	-	-	0.6	-	-	-	-	-	20	-	-	-	-	-	-	-	-
		max	63	0.4	0.4	0.4	1.8	1.8	0.4	0.05	0.02	0.5	40	-	-	-	-	-	-	-	-

Note

2 Nickel incluso nel conteggio del rame