



Ottone speciale - JIS H 2202:2016

Classificazione	Lega		Cu	Pb	Sn	Fe	Al	Ni	Mn	Sb	P	Si	Zn	S	As	Bi	Cd	Cr	Mg	Co	Se
JIS H 2202:2016	CACIN303	min	60	-	-	2	3	-	2.5	-	-	-	20	-	-	-	-	-	-	-	-
		max	65	0.2	0.5	4	5	0.5	5	-	-	0.1	40	-	-	-	-	-	-	-	-